

TEST REPORT

Report No. : MAN:HL:8480002136

DATE : 10th May, 2017



J.K. ENTERPRISES.
 4, BIRLA SHOPPING CENTER, OPP. NASIK ROAD COLLEGE, NASIK ROAD
 NASIK-422101
 INDIA
CONTACT PERSON : MR. SANJAY SAHNI

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED AND IDENTIFIED BY/ON BEHALF OF THE CUSTOMER AS :

SAMPLE DESCRIPTION	PLASTICS BASE DUAL RELEASE "GRAPAGE" GRAPE GUARD SHEET
STYLE NO.	23.5X32CM-5G, 23.5X35CM-5G, 23.5 X38CM-7G, 23.5X45CM-7G, 23.5X47CM-7G, 35X23.5CM-7G, 35X40CM-8.5G, 35X47CM-6.5G, 35X47CM-10G, 35X53.5CM-10G
SEASON	INDIAN SEASON 2017 - 18
COUNTRY OF ORIGIN	INDIA
SAMPLE RECEIVING DATE	14/04/2017
TEST PERFORMING DATE	18/04/2017 TO 10/05/2017

RESULT SUMMARY

TESTS NAME	COMMENTS
1. Testing as per Commission Regulation (EU) No 10/2011 of 14 January 2011 and hence Article 3 of European Regulation No. 1935/2004. (As per client's request)	---
Overall Migration	Pass
2. EN 71 Part 3 :2013 + A1 2014 –Migration of certain Elements (as per client's request)	Pass
3. Dimethyl Fumarate Content.	See Results
4. Mould Count	See Results

Per Pro SGS India Pvt Ltd.



Kapil Patil
Asst. Manager
 Email your Test Report Related Enquiries at Feedback.HLT@sgs.com

TEST REPORT

Report No. : MAN:HL:8480002136

DATE : 10th May, 2017



Test Results:

1 Overall Migration :

Method : With reference to EN 1186

Simulant Used	Test Condition	Result(mg/dm ²)	Permissible Limit(mg/dm ²)
		<u>1</u>	
3% Acetic Acid	40°C for 10 days	< 2	10
10% Ethnaol	40°C for 10 days	< 2	10
Comment	--	PASS	--

Sample Description :1. PLASTICS BASE DUAL RELEASE “GRAPAGE” GRAPE GUARD SHEET

- Note:
1. mg/dm² = milligram per square decimeter, mg/kg = milligram per kilograms
 2. °C = degree Celsius, < = less than
 3. MDL = Method Detection Limit, ND=Not Detected(<MDL)
 4. Test condition & simulant were specified by client
 5. Permissible Limit is according to Commission Regulation (EU) No 10/2011 of 14 January 2011 with amendments.
 6. Testing has been performed as per the Client's request.

2.DETERMINE THE DIMETHYL FUMARATE CONTENT :

Test Requested : To determine the Dimethyl Fumarate Contents in the submitted samples.

Test Method : In house method : Liquid extraction . Analysis was conducted by GC / MSD .

Test Result	: <u>Test</u>	<u>Result</u>	<u>Method Detection Limit(MDL)</u>
	Dimethyl Fumarate (mg/kg)	ND	0.1 mg/kg

Sample Discription : PLASTICS BASE DUAL RELEASE “GRAPAGE” GRAPE GUARD SHEET

Note:

- 1) ND = Not Detected
- 2) mg/kg = milligrams/kilogram
- 3) Above test has been subcontracted to SGS approved lab.
- 4) Testing has been performed as per client's request.

TEST REPORT

Report No. : MAN:HL:8480002136

DATE : 10th May, 2017



3. EN71-3: 2013 + A1 2014 – Migration of certain elements

Category III :

Method : With reference to EN71-3:2013 + A1 2014. Analysis of general elements was performed by ICP-OES.

Test Item	Results (mg/kg)	Reporting Limit (mg/kg)	Permissible Limit (mg/kg)
Mass of trace amount (mg)	--	--	--
Soluble Aluminium (Al)	ND	50	70,000
Soluble Antimony (Sb)	ND	10	560
Soluble Arsenic (As)	ND	10	47
Soluble Barium (Ba)	ND	50	18,750
Soluble Boron (B)	ND	50	15,000
Soluble Cadmium (Cd)	ND	10	17
Soluble Chromium (Cr)	ND	0.15	--
Soluble Chromium (III) [#] (Cr (III))	See Note#	1	460
Soluble Chromium (VI) [#] (Cr (VI))	See Note#	0.18	0.2
Soluble Cobalt (Co)	ND	10	130
Soluble Copper (Cu)	ND	50	7,700
Soluble Lead (Pb)	ND	10	160
Soluble Manganese (Mn)	ND	50	15,000
Soluble Mercury (Hg)	ND	10	94
Soluble Nickel (Ni)	ND	15	930
Soluble Selenium (Se)	ND	10	460
Soluble Strontium (Sr)	ND	50	56,000
Soluble Tin (Sn)	ND	4.9	180,000
Soluble Organic Tin [^]	See Note [^]	0.5	12
Soluble Zinc (Zn)	ND	50	46,000
Comment	PASS	--	--

Sample description: 1. PLASTICS BASE DUAL RELEASE "GRAPAGE" GRAPE GUARD SHEET

Note:

- 1) mg/kg = milligram per kilogram
- 2) ND = Not Detected
- 3) 1% = 10000 mg/kg = 10000 ppm
- 4) [#] Confirmation test of soluble chromium (III) & chromium (VI) is not required in case of soluble chromium does not exceed their requirements as specified in EN71-3: 2013+ A1 2014
- 5) [^] Confirmation test of soluble organic tin is not required in case of soluble tin, after conversion, does not exceed the soluble organic tin requirement as specified in EN71-3: 2013+ A1 2014
- 6) Testing has been performed as per client's request.

TEST REPORT

Report No. : MAN:HL:8480002136

DATE : 10th May, 2017



Test Results: 4.

S. No.	Test Name	Test Method Reference	Test Results	Unit
1	Mould Count	IS:5403:1999(Reaff. 2005)	<10	cfu/unit

Sample Discription : PLASTICS BASE DUAL RELEASE "GRAPAGE" GRAPE GUARD SHEET

Note: Above tests have been subcontracted to SGS approved lab.
CFU:Colony forming unit



*****End of Report*****